

(05/03)

BURNS, DOANE, SWECKER & MATHIS, L.L.P.

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

INSULATOR

P.O. Box 1450
Alexandria, VA 22313-1450

P.O. Box 1450
Alexandria, VA 22311

P.O. Box 1450
Alexandria, VA 22313-1450

Robert S. Swecker
Registration No. 19,885

(703) 836-6620

(05/03)

(05/03)



Eur päisches
Patentamt

European
Patent Office

Office européen
des brevets

Bescheinigung Certificate Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglichen eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°
02405675.6

Der Präsident des Europäischen Patentamts;
im Auftrag
For the President of the European Patent Office
Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Anmeldung Nr.: 02405675.6
Application no.: 02405675.6
Date of filing: 02.08.02
Anmeldetag:
Date de dépôt:

Anmelder/Applicant(s):

ABB RESEARCH LTD.
Affolternstrasse 52
8050 Zürich
SUISSE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Solid insulator and method for manufacturing a solid insulator

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

H01B3/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignés lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

Solid insulator and method for manufacturing a solid insulator

5

DESCRIPTION

TECHNICAL FIELD

10

The invention relates to a solid insulator in accordance with the preamble of the first claim.
It likewise relates to a method for manufacturing a solid insulator in accordance with the preamble of the independent method claim.

15

BACKGROUND OF THE INVENTION

In pressurized gas-insulated switchgear stations, the solid insulation components are disc-like in shape with some complex sub-structural features including central metallic inserts.

20

DE 33 11 218 A1 discloses a disc-type insulator for enclosed high-voltage equipment. The insulator includes a cast-in electrode which is segmented and which extends peripherally and concentrically with respect to the edge surface of the disc. The cast-in electrode is connected to contact electrodes by means of contact tongues; the contact electrodes bearing against a metal mounting ring. To avoid damage to the disc-type insulator, to the contact tongues, or to the cast-in electrode during shrinkage of the disc-type insulator, following its casting, or damage resulting from thermal stresses during operation, the cast-in electrode is divided

30

25

into a plurality of electrode segments which follow one another in the peripheral direction.

DE 40 15 929 A1 discloses a solid insulator, which is intended for a gas-insulated metal-encapsulated high-voltage installation. It has an insulator body containing a cast resin, an electrode, which is supported by the insulator body and is provided for carrying high voltage, a retaining part which can be mounted on the metal encapsulation and a field control element, which is cast onto the insulator body and consists of electrically conductive plastic. The insulator is intended to reliably prevent mechanical damage to the insulator body and / or irreversible damage caused by long-term dielectric stresses.

Such disk-like insulation components consist of a vacuum-cast, mineral-filled (i.e. SiO_2 , Al_2O_3 or CaSiO_3), anhydride-cured Bisphenol-A epoxy, sustaining the current mechanical and electrical loads. In gas insulated switchgear substations, solid insulation components are submitted to both high electrical field and high mechanical loads, such as hydrostatic pressures and bending moments.

The main drawbacks of mineral-particle-filled epoxy gas insulated switchgear insulators are the heavy weight of such components (e.g. two to three people are required to handle the biggest insulators, i.e. more than 30 kg), the limited mechanical performance and relative brittleness of the material, leading to catastrophic failure mechanisms.

SUMMARY OF THE INVENTION

Accordingly, one object of the invention is to provide a solid insulator, which is lightweight and has a high mechanical performance.

According to the invention, this is achieved by the features of the first claim.

- The advantages of the invention can be seen, inter alia, in the fact that weight can be saved up to 70% compared to conventional mineral-particle-filled epoxy materials, which allows an easier handling and cheaper maintenance, requiring fewer personnel. A further advantage is the much better mechanical (i.e. stiffness and strength) performance, which can lead to thinner structures and hence allow more compact gas insulated switchgear substation designs. It also can lead to higher flexibility in the solid insulator design, allowing more simple design geometry, such as a flat-disc shape, which is certainly the best possible dielectric design for gas insulated switchgear solid insulators. Further the fields of application will be larger, since the new materials can meet the requirements of some specific local regulations for very high burst-pressure solid insulators, as well as for the latent SF₆-free insulation technology, for which much higher operating pressures will be required. No catastrophic failure mechanism applies, meaning a higher reliability and safety. The thinner insulator design allowed by the new solid insulator technology will avoid the fastidious and thus expensive integration of complex field grading electrodes as described in DE 33 11 218 A1 and DE 40 15 929 A1 in most cases. In cases where field grading electrodes are really required, the easy and simple integration of conductive fibers, such as carbon fibers, is however possible.
- 20 The use of fiber-reinforced epoxy materials will lead to an overall cost reduction in gas insulated switchgear solid insulators by bringing higher mechanical performances linked with a higher reliability.
- 25 Further advantageous embodiments of the invention emerge from the subclaims.
- 30

DESCRIPTION OF THE DRAWINGS

A more complete appreciation of the invention and many of the attendant advantages thereof will be readily obtained as the same becomes better understood by reference to the following detailed description when considered in connection with the accompanying drawings, wherein:

- 5 Fig. 1 shows a radial and hoop orientation fiber fabric type;
 Fig. 2 shows a typical laminate layer stacking sequence using the radial and
 hoop orientation fiber fabric type from Fig. 1;
 Fig. 3 shows a biaxial orientation fiber fabric type;
 Fig. 4 shows a typical laminate layer stacking sequence using biaxial orienta-
 tion fiber fabric types from Fig. 3;
 Fig. 5 shows an unidirectional orientation fiber fabric type;
 Fig. 6 shows a typical laminate layer stacking sequence using the unidirectional
 orientation fiber fabric type from Fig. 5;
 Fig. 7 shows a three-dimensional orthogonal fiber weaving architecture;
 Fig. 8 shows a continuous spiral-like preform for radial and hoop fiber orienta-
 tion;
 Fig. 9 shows the equipment needed for the Resin Transfer Molding (RTM)
 technology;
 Fig. 10 shows the process for the Resin Transfer Molding (RTM) technology;
 Fig. 11 shows a flat-disc-shape geometry of a fiber-reinforced epoxy gas insu-
 lated switchgear solid insulator with a radial and hoop fiber orientation;
 Fig. 12 shows stiffness-to-weight and strength-to-weight ratios of glass-fiber rein-
 forced epoxy resins compared to aluminum, steel, neat epoxy, and min-
 eral-particle-filled epoxy materials.
- 20 Fig. 9 shows the equipment needed for the Resin Transfer Molding (RTM)
 technology;
 Fig. 10 shows the process for the Resin Transfer Molding (RTM) technology;
 Fig. 11 shows a flat-disc-shape geometry of a fiber-reinforced epoxy gas insu-
 lated switchgear solid insulator with a radial and hoop fiber orientation;
 Fig. 12 shows stiffness-to-weight and strength-to-weight ratios of glass-fiber rein-
 forced epoxy resins compared to aluminum, steel, neat epoxy, and min-
 eral-particle-filled epoxy materials.
- 25 Fig. 12 shows stiffness-to-weight and strength-to-weight ratios of glass-fiber rein-
 forced epoxy resins compared to aluminum, steel, neat epoxy, and min-
 eral-particle-filled epoxy materials.
- 30 Only those elements that are essential for an understanding of the invention are
 shown.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

5 Fiber-reinforced polymers are an unique class of materials, which are composed of a polymeric matrix material reinforced with organic or inorganic fibers. The reinforcing fibers are the primary load carriers, with the matrix component transferring the load from fiber to fiber. In the present description, the polymeric matrix consists of a typical anhydride-cured epoxy resin commonly used in electrical insulation, while the nature of the reinforcing fibers can be of various types, as long as it involves good electrical insulation properties. Glass fibers in general, with a preference for the E-CR glass fiber type, are certainly the most suited fibers for the present solid electrical insulation application. However, other inorganic fibers, such as basalt and quartz fibers, and organic fibers, such as liquid crystal polymer, aromatic polyamide and poly(p-phenylene-2,6-benzobisoxazole) fibers can also be used. Additionally, reinforcement of the polymeric matrix may be achieved in a variety of ways. Fibers may be either continuous, in the form of woven or knitted fabrics or three-dimensional preforms, or discontinuous, in the form of mats. Fiber-reinforced epoxy materials offer some significant advantages over the conventional vacuum-cast mineral-particle-filled epoxy materials. The strength-to-weight and stiffness-to-weight ratios are the primary reasons fiber-reinforced polymers are used. Additionally, the fracture toughness of glass-fiber-reinforced epoxy materials is much better than mineral-particle-filled epoxy materials. Consequently, glass-fiber reinforced epoxy materials greatly alter the catastrophic failure mechanisms involved in mineral-particle-filled epoxy materials. Only inter-laminar failure or delamination between fibers and the epoxy matrix may occur. Furthermore, the fracture toughness of fiber reinforced polymeric materials can be maximized by an appropriate fiber orientation.

30 Solid insulation components in pressurized SF₆-gas insulated switchgear stations are basically circular bulkheads between two pressurized chambers. Such gas insulated switchgear stations are described in DE 33 11 218 A1 and DE 40 15 929 A1, which are enclosed herewith. The main load that these solid insulators are inclined to experience is a typical isostatic-pressure load type. There is basically no

5 preferred in-plane load direction. Quasi-isotropic properties, i.e. in-plane properties identical in all directions, are therefore required in such a load case. Quasi-isotropic laminate properties can be achieved using mainly three different fiber fabric architectures, namely radial and hoop fiber orientation, biaxial fiber orientation with layer rotation and unidirectional (UD) fiber orientation with layer rotation. These different fiber fabric architectures can also be mixed.

10 Radial and hoop fiber orientation:
The radial and hoop fiber orientation, as shown in Figure 1, is the best fiber orientation alternative, since the quasi-isotropic property requirement is by definition already achieved with this fiber orientation type. Different layers of such a fiber fabric can then be simply stacked to form the fiber backbone of the insulator, as shown in Figure 2.

15 Biaxial fiber orientation with layer rotation:
Quasi-isotropic laminate properties can also be achieved using biaxial orientation fiber fabric types, such as two dimensional woven fabrics, as shown in Figure 3, provided each stacked fabric layer is rotated by a given degree (the lower, the more quasi-isotropic) compared to the previous one, as shown in Figure 4. A 360° total rotation should ideally be achieved in the layer stacking sequence.

20 Unidirectional (UD) fiber orientation with layer rotation:
A similar approach as with rotated biaxial fiber fabrics can be used with unidirectional (UD) fiber fabrics, as shown in Figure 5, instead. Quasi-isotropic laminate properties are also achieved by rotating the different UD fabric layers, as shown in Figure 6. Again, the lower the rotating angle, the more quasi-isotropic the properties. A 360° total rotation should here also ideally be achieved in the layer stacking sequence.

Fiber reinforcement backbone preforming:

The two-dimensional or UD fiber structures mentioned above are assembled in a preform. A preform is a single piece of reinforcement pre-tailored to the shape of the part to be manufactured. In the present description, disc-like shape preforms are used. The biaxial woven or UD fabrics are cut. This operation is not necessary for the radial and hoop orientation fabrics, since they are already weaved in a disc-like shape. The layers are then physically bonded, i.e. stitched, or chemically bonded, i.e. using resin powders, to provide the final shape. The use of fiber preforms lead to significant manufacturing time reductions and quality improvements, since the fastidious laminating operation is avoided. Three dimensional woven fiber structures, as shown in Figure 7, can also be used as preforms. Instead of a stitching or bonding operation, a third weave dimension is added. As a result, three dimensional fiber structures have the further advantage of dramatically mitigating inter-laminar failures, which represent the most critical failure mechanism in fiber-reinforced polymer materials. In the radial and hoop fiber orientation case, continuous spiral-like preforms, as shown in Figure 8, are also alternative solutions to stitched or bonded two dimensional woven fabric preforms.

Manufacturing process:

20 The fiber-reinforced epoxy gas insulated switchgear insulators are manufactured using the Resin Transfer Molding (RTM) processing technology. RTM-type infusion processes, as shown in Figure 9 and 10, are multiple stage processes, which involve the placement of a fiber preform into a matched mold tool and the closing of the mold followed by the injection of a sufficient quantity of the epoxy matrix at low pressure, typically 1-4 bar, into the closed mold cavity thus permeating the fiber pack. As shown in Figure 9, the epoxy resin is mixed with the anhydride-based hardener or catalyst prior to the injection into the mold. Once the epoxy matrix has cured, the mold is opened and the part is removed. RTM-type infusion processes are best known for their abilities to provide an excellent surface finish, a near-net-shape part which requires little finishing, and composite properties often comparable to vacuum bagged or autoclaved composites, i.e. with very low void content. Additionally, polymeric gel coats can be applied in RTM technology in order to fur-

ther improve the surface aspect quality of the final part, which can be of very high importance in electrical applications. Furthermore, a low-permittivity gel coat can also be tailored in order to reduce the particle sensitivity of the insulator surface in an aggressive gaseous environment. The RTM-type processes fall into categories, which involve pushing the resin into the cavity with external pressure (RTM-type) and those, which pull the resin in by vacuum process (VARTM-type). Pending on the solid insulator type, vacuum can be applied instead of or in combination with external pressure in order to insure a very low / near zero void content within the part, which is an absolute prerequisite in high-voltage insulation applications.

Figure 11 shows a flat-disc-shape geometry of a fiber-reinforced epoxy gas insulated switchgear solid insulator with a radial and hoop fiber orientation after processing. A preform consisting of different stacked layers with radial and hoop fiber orientation, as shown in Figures 1 and 2, is used.

Figure 12 shows the strength-to-weight and stiffness-to-weight ratios of different materials. These two ratios are clearly much better for epoxy resins reinforced with glass fibers than for epoxy resins filled with mineral particles.

The invention is of course not restricted to the exemplary embodiment shown and described. Obviously, numerous modifications and variations of the present invention are possible in light of the above teachings. It is therefore to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described herein.

1.	5	Solid insulator for gas-insulated encapsulated high voltage installations with an insulator body which is supporting at least one conductor that is provided for carrying high voltage and that is arranged in an outer enclosure, wherein said insulator body comprises a fiber-reinforced polymer.
2.	10	Solid insulator as claimed in claim 1, wherein said insulator body comprises a fiber-reinforced epoxy material.
3.		Solid insulator as claimed in claim 1 or 2, wherein said insulator body comprises non-conductive organic fibers and / or non-conductive inorganic fibers.
4.	15	Solid insulator as claimed in claim 1, 2 or 3, wherein said insulator body comprises conductive fibers for field grading purposes.
5.	20	Solid insulator as claimed in the preceding claims, wherein the orientation of the fibers in the insulator body is such that quasi-isotropic mechanical properties of the insulator body are achieved.
6.	25	Solid insulator as claimed in claim 5, wherein the orientation of the fibers in the insulator body is in radial and hoop direction and the fiber fabrics are arranged in different layers.
7.	30	Solid insulator as claimed in claim 5 or 6, wherein the orientation of the fibers in the insulator body is biaxial and the fiber fabrics are arranged in different layers; the stacked layers being rotated by a given degree.

PATENT CLAIMS

8. Solid insulator as claimed in claim 5, 6, or 7,
wherein the orientation of the fibers in the insulator body is unidirectional
and the fiber fabrics are arranged in different layers; the stacked layers be-
ing rotated by a given degree.
9. Solid insulator as claimed in claims 5 - 8,
wherein the fiber backbone of the insulator body comprises a preform with
stacked layers of radial and hoop, biaxial or unidirectional fibers, where the
layers are physically or chemically bonded.
10. Solid insulator as claimed in one of the claims 5 - 8,
wherein the fiber backbone of the insulator body comprises a preform,
which comprises a continuous radial and hoop spiral-like fiber layer.
11. Solid insulator as claimed in one of the claims 5 - 8,
wherein the fiber backbone in the insulator body comprises a preform,
which comprises a three-dimensional woven fiber structure.
12. Method for manufacturing a solid insulator for gas-insulated encapsulated
high voltage installations with an insulator body which is supporting at least
one central conductor that is provided for carrying high voltage and that is
arranged in an outer enclosure, including the steps of:
arranging the fibers in a mold,
closing the mold and infusing the polymeric matrix into the mold by using
low pressure and / or vacuum,
curing the polymeric matrix in the mold,
removing the insulator body from the mold.
13. Method for manufacturing a solid insulator as claimed in claim 12,
wherein the fibers are inserted into the mold as a preform.

ABSTRACT

5 Solid insulator for gas-insulated encapsulated high voltage installations with an insulator body, which is supporting at least one central conductor that is provided for carrying high voltage and that is arranged in an outer enclosure. The insulator body comprises a fiber-reinforced polymer.

10

(Fig. 11)




Fig. 1




Fig. 2




Fig. 3




Fig. 4

Fig. 6




Fig. 5




Fig. 8




Fig. 7




Fig. 10




Fig. 9

